



CROWN GENERAL N.V.

Havenlaan 2 - 3980 Tessenderlo - Belgium

Tel: +32 13 66 17 51 - Fax: +32 13 66 88 18

Email: info@crowngeneral.be

Product Specifications

PVC-FOAM D.170/200 SR (Slow Recovery)

<u>PARAMETERS</u>	<u>UNIT</u>	<u>VALUE</u>	<u>NORM</u>
Density	kg/m ³	170-200	
Tensile Strength	Kpa	≥ 275	DIN 53571
Elongation at Break	%	≥ 120	DIN 53571
Tear Strength	N/mm	≥ 1,1	DIN 53515
Compression Set (50%/23°C/72h)	%	≤ 30	DIN 53572
Compression Deflection	Kpa	0 s. 25-50 60 s. 10-35	ASTM 1667
Shore 00 Hardness		25-50	
Waterabsorption	%	≤ 15	
Compression Waterseal		≥ 20 %	U-TEST
Flammability	mm/min	≤ 100 (≥ 4mm)	FMVSS 302
Temperature Range	°C	-30 / +60	
Tolerance: At G > 500 g/m ² : +/-10 % At G ≤ 500 g/m ² : +/-20 % G = weight	-	-	-

Products with different technical characteristics can be developed and manufactured at request. The above data are only for information and do not involve any guarantee. As our products are used for many purposes, we recommend our customers to do their own tests to determine the suitability of our products for their purposes and applications.